

# CRYSTAL CLEAR-55

CL



- IPL LIFE - CRYSTAL - CLEAR 55 - USP

- 药品级标准, TPE卫生材质、无硫化。专为蠕动泵设计, 无任何污染风险

## 颜色:

- 半透明

## 温度:

- -20°C + 80°C

## 应用:

- 为制药、化妆品及食品行业的蠕动泵特别设计。
- 可应用于液体药物的精密分注, 灌装及配药系统, 细胞培养、净化及分离过程, 实验室的各类应用中。此外, 如香皂、护肤霜, 清洁剂的分注中。
- 分注饮料、果汁、酒精(最高浓度可达 50%)、酱料、粘性液体(如糖浆)、纯净水。

## 技术特性:

- 非常纯净、卫生的TPE材质、无硫化, 没有污染风险。
- 低孔隙度, 减少渗透问题, 保留传输物质的原有属性。
- 内、外壁完全光滑, 提高流量, 降低阻塞的可能性, 也便于清洁。
- 良好的耐化学品性能, 耐酸、碱性溶液, 耐水解、抗菌。

## 标准:

- 符合 ISO 10993-5 (非细胞毒性), ISO10993-4 (非溶血性, 直接或间接) 标准, 符合USP <88> CLASS VI级药品级规定, 符合USP <661> 理化塑料测试标准, 符合EU Regulation n° 10/2011食品级标准, 符合 FDA regulations (Title 21 CFR 177.2600 含水食品) 标准。

- Pharma.Hygienic TPE pharma-grade tuding for peristaltic pumps.Curing-free material

## Colour:

- Translucent

## Temperature range:

- -20°C + 80°C

## Applications:

- Ideal solution for peristaltic pumps in pharmaceutical, cosmetic and food sectors.
- Dosing of pharmaceutical fluids, filling and dispensing systems, cell culture media, purification and separation processes, laboratory. Dosing of soaps, creams, detergents.
- Dosing and dispenser of beverages, juices, alcohols (up to max 50% concentration), sauces, viscous fluids (syrups), purified waters.

## Technical features:

- Extremely pure and hygienic TPE, curing-free (no vulcanization process, no risk of leaching).
- The low porosity, reduces permeation problems and preserves the organoleptic properties of the media.
- Completely smooth inside and outside to enhance the flow, detect possible blockages and to allow easy cleaning process.
- Good chemical resistance to acids, alkaline solutions, hydrolysis, microbes and bacteria proliferation.

## Standards:

- ISO 10993-5 (Non cytotoxic), ISO10993-4 (Non hemolytic, direct and indirect methods, USP <88> CLASS VI, USP <661> Physicochemical Tests-plastics, EU Regulation n° 10/2011, FDA regulations (Title 21 CFR 177.2600 for aqueous foods).



# CRYSTAL CLEAR-55

CL

代码 Part number	内径Φ Inside Φ (mm)	外径Φ Outside Φ (mm)	壁厚 wall th. (mm)	重量 Weight (g/m)	工作压力 Working press. (Bar)	耐负压 Vacuum (mH2O)	弯曲半径 Bending radius (mm)	每卷长度 Roll length (m)	包装 Package (m3)
CLN900320064	3.2/ 1/8"	6.4/ 1/4"	1.6	20	0.9	640	12.8	15.2	min 10 boxes
CLN900320080	3.2/ 1/8"	8/ 5/16"	2.4	40	1.1	680	12.8	15.2	min 10 boxes
CLN900480080	4.8/ 3/16"	8/ 5/16"	1.6	30	0.9	540	19.2	15.2	min 10 boxes
CLN900480095	4.8/ 3/16"	9.5/ 3/8"	2.4	50	0.9	540	19.04	15.2	min 10 boxes
CLN900630095	6.35/ 1/4"	9.5/ 3/8"	1.6	35	0.7	410	31.75	15.2	min 10 boxes
CLN900630111	6.35/ 1/4"	11.1/ 7/16"	2.4	60	1.1	640	31.75	15.2	min 10 boxes
CLN900630127	6.35/ 1/4"	12.7/ 1/2"	3.2	85	1.2	680	38.1	15.2	min 10 boxes
CLN900790111	7.9/ 5/16"	11.1/ 7/16"	1.6	40	0.6	260	55.3	15.2	min 10 boxes
CLN900790127	7.9/ 5/16"	12.7/ 1/2"	2.4	70	0.9	450	63.2	15.2	min 10 boxes
CLN900950127	9.5/ 3/8"	12.7/ 1/2"	1.6	50	0.5	225	66.5	15.2	min 10 boxes
CLN900950143	9.5/ 3/8"	14.3/ 9/16"	2.4	80	1	600	52.25	15.2	min 10 boxes
CLN700950127	9.5/ 3/8"	12.7/ 1/2"	1.6	50	0.5	225	66.5	7.5	min 15 boxes
CLN700950159	9.5/ 3/8"	15.9/ 5/8"	3.2	115	1	600	52.25	7.5	min 15 boxes
CLN701270175	12.7/ 1/2"	17.5/ 11/16"	2.4	100	0.6	430	76.2	7.5	min 15 boxes
CLN701270191	12.7/ 1/2"	19.1/ 3/4"	3.2	140	0.9	410	76.2	7.5	min 15 boxes

\* Available on request, contact our sales office for more info and quantities

\* 如有需要, 请与我们的销售办公室联系以获取更多信息和数量

The technical data here reported were measured at 23° c with 50% humidity

技术参数均在23°C 50%湿度下测量

